International Journal of Luminescence and Applications Vol.1 (II)

Photoluminescence Study of Rare Earth Doped Nano Sr₂CeO₄ Phosphor

Ch. Atchyutha Rao^{1*}, K.V.R.Murthy², N.V.Poornachandra Rao³, K.Suresh⁴

^{*1}Department of Physics, VRS & YRN College, Chirala -523 155, A.P, India

²Display Materials Laboratory, Applied Physics Department, Faculty of Technology & Engineering,

M.S University of Baroda, Baroda – 390 001, India

³ NVR College of Engineering and Technology, Tenali – 522 201, Guntur District, A.P, India

⁴Department of physics, CSR Sarma College, Ongole-523001, A.P, India

*Corresponding author. Tel.: +919949522835

E-mail address: atchyuth 1674@yahoo.co.in

Abstract

Photoluminescence (PL) studies of undoped Sr_2CeO_4 blue nano phosphor and doped with La, Eu and Dy rare earth ions of 0.5% concentration in Sr_2CeO_4 phosphor samples are reported in the present paper. All the samples were prepared through standard solid state reaction method. All the required chemicals were weighted for molar concentration and thoroughly mixed in agate mortar and pestle. The final mixture was heated at 1200 °C for 3 hour. The received sintered material is a hard cake and looks as light cream colour. The XRD study reviles the formation of nano particles (~ 9nm). The PL was recorded with 250nm excitation and the PL emission was observed at 470 for pure specimen and for doped with Dy the PL emission was reduced to 10%. When doped with La and Eu the PL emission was mainly concentrated at 470 with many allowed emission peaks of La and Eu. From this study it can be inferred the solid state reaction method is adequate for synthesis of Sr_2CeO_4 nano particles.

Keywords: photoluminescence; solid state reaction method; Phosphor; nano particles.

1. INTRODUCTION

At present, we are living in a transition period toward reaction, flat panel displays, and CRTs are being more and more calcinations, pulsed laser deposition, polymeric replaced by other technologies, in particular, liquid precursors and ultrasonic spray pyrolysis method [1-4]. crystal displays (LCDs) and plasma display panels In this work, fine particles of the undoped blue (PDPs). The most promising technology for screen Sr₂CeO₄ phosphor doped with La, Eu and Dy rare sizes larger than 40 inch is the PDP. Satisfactorily earth ions are prepared via solid state reaction method produced red and green commercial materials many and spectroscopic study on all the samples are researchers, but comparable materials for the blue reported. emission are still lacking and are under development for practical applications. Even in the paper industry, 2. MATERIALS AND METHOD fluorescent dyes that absorb UV and emit in blue color are widely used as organic optical brightening agents Analytical grade Strontium nitrate [Sr(NO₃)₂], Cerium (OBA) and new inorganic ones have been under oxide (CeO₂), Lanthanum oxide (La₂O₃), Europium investigation. Concerning many of these applications, oxide (Eu2O3) and Dysprosium oxide (Dy2O3) of such as FED and OBA, the availability of phosphor assay 99.9% were used as starting materials. All the systems consisting of uniform particles in size and phosphor samples are prepared via solid state reaction shape is also an essential prerequisite for improved method (SSR). performance, and new synthetic routes are been developed in order to reach these systems. Recently, a First we prepared undoped Sr₂CeO₄ phosphor by new promising blue phosphor, Sr₂CeO₄, was weighing, mixing inorganic salts, Strontium nitrate

developed by combinatorial synthesis and prepared by different routes, such as conventional solid state co-precipitation, microwave chemical

International Journal of Luminescence and Applications Vol.1 (II)

We ground into fine powder using agate mortar and average particle diameter of Europium doped phosphor pestle about an hour. The samples were fired at 1200 is 17 um and the crystallite size is around 9nm. As such °C for 3 hours with a heating rate of 4° C/min in a many particles agglomerate and from as a crystallite muffle furnace by keeping in an alumina crucible [5, many crystallite together becomes a particle 6]. In the same way La, Eu and Dy rare earth ions approximately 2000 crystallites (9 nm) together forms doped in Sr_2CeO_4 phosphor concentration (0.5 mol %) a particle of diameter is $17\mu m$ in Eu doped Sr_2CeO_4

All the phosphor samples were characterized by X-ray diffractometry using (Synchrotron Beam line), Particle size analysis was done using, laser particle size analyzer Malvern Instrument Ltd (U.K) and Photoluminescence studies using (SHIMADZU RF5301 PC), recorded at room temperature.

3. RESULTS AND DISCUSSION

3.1 Physical properties

After heating at 1200° C and cooling to room temperature in the furnace, the samples appear light cream in colour and hard crystalline material was received. All the samples were again ground using agate motor and pestle to make uniform powder.

3.2 X-ray Diffractometry (XRD)

XRD of the present material were done on Indus beam line at RRCAT Indore. The wave length of $(0.89A^{\circ})$.Fig.1 is the XRD pattern of undoped Sr₂CeO₄ phosphor. On comparison with literature most of the peaks are matching and the majority of the material in single phase and is well agreement with the findings of the previous workers like Chia-Hao-Hsu et. al. [7]. The calculated crystallite size using Scherer's formula (t =K. λ \Bcos θ) for undoped Sr₂CeO₄ is around ~ 9nm. This confirms the formation of nano phosphor, via solid state method [8].



Fig.1: XRD Pattern of Sr₂CeO₄

3.3 Particle size Analysis

[Sr(NO₃)₂], Cerium oxide (CeO₂) in 2:1 molar ratio. 18.31µm, Eu: 17µm, Dy: 32µm from the above data the



Fig.2 undoped Sr₂CeO₄



Fig.3 Eu doped Sr₂CeO₄



Fig.4 Dy doped Sr₂CeO₄

3.3 Photoluminescence Study

The prepared phosphor specimen particle size was measured by using laser based system Malvern Instrument U.K as shown in the fig. The mean diameter of the particle size as follows. Sr₂CeO₄:26µm, La:

Fig.5 shows PL emission spectrum of undoped Sr₂CeO₄ phosphor, it is observed that under 250nm excitation, phosphor shows broad emission from 350 -

International Journal of Luminescence and Applications Vol.1 (II)

650 peaking at 470nm. This broad band is due to concentrations of Eu ion the emission, red color $f \rightarrow t_1 g$ transitions of Ce⁴⁺. When excitation was varied, dominates.

the observed emission is same but intensity is high for 260nm excitation only. Here we observed the crystal field around 370nm wavelength with high intensity, when compared with the pervious works.



Fig.5: Emission Spectrum of undoped Sr₂CeO₄ at 250nm excitation



Fig.6: Excitation Spectrums of La, Eu & Dy (0.5%) doped Sr₂CeO₄

Fig.7 shows the PL emission of Eu and Dy rare earth ions doped keeping Dy 0.5% concentration at constant, varying the Eu concentrations from 0.01 -1% a shown in the fig.7 in Sr₂CeO₄ phosphor. Under 270nm Faculty Development Programme (FDP). excitation, we observed that when La is doped the emission spectrum is same as undoped Sr₂CeO₄ phosphor along with same crystal field which is not [1] Pallavi Page and Murthy, K.V.R., Philosophical shown in the fig. In the case of Eu we observed that, all the transitions of Eu ion are not observed at 0.01 and 0.1 concentrations, whereas the Dy peak at 575nm is well resolved with high intensity. When the Eu Phosphors, Phenomenon and Applications, Nova Sci. concentration increases further the peaks are resolving Publishers, NY (USA) 2008 well, consequently the fall of 575nm peak of Dy ion is observed. Finally concluded that at higher



Fig.7: Emission Spectrum of Eu (0.01, 0.1, 0.2, 0.5 &1%) & Dy (0.5%) doped Sr₂CeO₄ under 270nm excitation

Where as Dy ion shows 470 & 575nm emission peaks (curve 1), without showing crystal field. We also observed the emission spectra under different concentrations and at different excitations. Overall the samples shows emission intensity is high at 0.01% concentration under 260nm excitation wavelength.

4. CONCLUSIONS

The present phosphor under study can be a good material for many display devices. The calculated average crystallite size using Scherer's formula is ~9nm. This confirms the formation of nano phosphor with good PL intensity under 270nm excitation.

AKNOWLEDGEMENT

The author gratefully thanks the University Grants Commission, New Delhi, for financial support under

REFERENCES

Magazine Letters, Vol. 90, No. 9, September 2010, 653-662

[2] Lakshmanan, A. R. Luminescence and Display

International Journal of Luminescence and Applications Vol.1 (II)

[3] Kummer, F. The production of fluorescent lamp phosphors, in Proc. Physics and chemistry of luminescent materials, Struck, C.W., Misra, K.C. and Barolo, B.Di., Eds., Electrochem. Soc. Pennington (NJ), 210, 1999.

[4] Rao, R.P. J. Electrochem. Soc. 143, 189, 1996

[5] Bechtel, H., Justel, T., Glaser, H. and Wiechert, D.U., J. SID, 10, 63, 2002.

[6] Blasse, G. and Grabmaier, B.C. Luminescent Materials, Springer-Verlag, Berlin (Germany) 1994.

[7] Chia-Hao-Hsu et. al. ICSD Card No.89-6654

[8] Pallavi Page, Rahul Ghildiyal, Murthy, K.V.R. Materials Research Bulletin, Vol.41,10, (2006),1854-1860.